

**This Page Is Inserted by IFW Operations
and is not a part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- **BLACK BORDERS**
- **TEXT CUT OFF AT TOP, BOTTOM OR SIDES**
- **FADED TEXT**
- **ILLEGIBLE TEXT**
- **SKEWED/SLANTED IMAGES**
- **COLORED PHOTOS**
- **BLACK OR VERY BLACK AND WHITE DARK PHOTOS**
- **GRAY SCALE DOCUMENTS**

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

(54) LONG-LIFE COOLANT COMPOSIT OR LIQUID-COOLED INTERNAL COMBUSTION ENGINE

- (11) 4-279690 (A) (43) 5.10.1992 (19) JP
 (21) Appl. No. 3-41872 (22) 7.3.1991
 (71) SEKIYU SANGIYOU KATSUSEIKA SENTAA(1)
 (72) NOBORU MIZUTANI(2)
 (51) Int. Cl.⁵ C09K5/00

PURPOSE: To provide the subject composition composed mainly of a specific glycol, containing a rust-proofing agent and hydrazine, stable over a long period even under a high-temperature condition and having excellent heat and corrosion resistances.

CONSTITUTION: The objective composition contains (A) preferably about 0.1-7wt.% (especially about 0.5-6wt.%) of a rust-proofing agent composed of mercaptobenzothiazole, methylbenzotriazole, alkylimidazoline, etc., (B) preferably 0.001-1wt.% (especially about 0.01-0.05wt.%) of hydrazine and (C) preferably about 90-99.899wt.% of a 2-9C glycol as a main component. The composition is added to an antifreezing fluid or coolant at a ratio of preferably about 10-50wt.% (especially about 20-40wt.%).

(54) PHOTOCHROMIC FINE POWDER AND ITS PRODUCTION

- (11) 4-279691 (A) (43) 5.10.1992 (19) JP
 (21) Appl. No. 3-123274 (22) 6.3.1991
 (71) ISHIHARA SANGYO KAISHA LTD (72) MASATAKE MARUO(1)
 (51) Int. Cl.⁵ C09K9/02

PURPOSE: To obtain the subject fine powder applicable to the surface of an element substrate or chargeable to a substrate as a photochromic color rendering material by supporting a photochromic organic compound on the surface of ultrafine particles of a specific inorganic compound.


CONSTITUTION: The objective fine powder can be produced by supporting (A) a photochromic organic compound such as spiropyran compound, spirooxazine compound, dithizone metal complex, dihydropyrene compound, triphenylmethane compound, diaryl ethene compound, fulgide compound, diazobenzene compound and thioindigo compound on the surface of (B) ultrafine particles of a transparent inorganic compound having a specific surface area of $\geq 50\text{m}^2/\text{g}$ (preferably $\geq 100\text{m}^2/\text{g}$), e.g. hydrated titanium dioxide (e.g. metatitanic acid), colloidal silica and aluminosilicate (e.g. zeolite).

(54) FLUORESCENT POWDER AND ITS PRODUCTION

- (11) 4-279692 (A) (43) 5.10.1992 (19) JP
 (21) Appl. No. 3-65435 (22) 6.3.1991
 (71) MIYOTA K.K. (72) RYUJI OZAWA
 (51) Int. Cl.⁵ C09K11/00, H01J29/20

PURPOSE: To provide a new fluorescent powder necessary for improving the resolution and brightness of the fluorescent film of a cathode-ray tube.

CONSTITUTION: Each of primary particles constituting the objective fluorescent powder is made of a polycrystalline material and has a nearly spherical form having rough surface. The use of a flux to increase the growth rate of the particle is necessary for the production of the particle. The surface of the obtained particle can be roughened by uniformly etching with an acid having a proper concentration. The etched surface is stabilized with phosphoric acid. The fluorescent powder produced by this process exhibits excellent flowability and gives a fluorescent film having remarkably improved resolution and brightness.



(a): Particle diameter μm (microscope), (b): Heating temperature $^{\circ}\text{C}$

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 04-279690

(43)Date of publication of application : 05.10.1992

(51)Int.Cl.

C09K 5/00

(21)Application number : 03-041872

(71)Applicant : SEKIYU SANGYO KASSEIKA CENTER
COSMO OIL CO LTD

(22)Date of filing : 07.03.1991

(72)Inventor : MIZUTANI NOBORU
KANAI SAKUNOBU
YAMADA SHIGEHISA

(54) LONG-LIFE COOLANT COMPOSITION FOR LIQUID-COOLED INTERNAL COMBUSTION ENGINE

(57)Abstract:

PURPOSE: To provide the subject composition composed mainly of a specific glycol, containing a rust-proofing agent and hydrazine, stable over a long period even under a high-temperature condition and having excellent heat and corrosion resistances.

CONSTITUTION: The objective composition contains (A) preferably about 0.1-7wt.% (especially about 0.5-6wt.%) of a rust-proofing agent composed of mercaptobenzothiazole, methylbenzotriazole, alkylimidazoline, etc., (B) preferably 0.001-1wt.% (especially about 0.01-0.05wt.%) of hydrazine and (C) preferably about 90-99.899wt.% of a 2-9C glycol as a main component. The composition is added to an antifreezing fluid or coolant at a ratio of preferably about 10-50wt.% (especially about 20-40wt.%).

H₂O

BEST AVAILABLE COPY

(19) 日本国特許庁 (J P)

(12) 公開特許公報 (A)

(11) 特許出願公開番号

特開平4-279690

(43) 公開日 平成4年(1992)10月5日

(51) Int.Cl.⁵

C 0 9 K 5/00

識別記号

庁内整理番号

F I

技術表示箇所

C 8930-4H

審査請求 未請求 請求項の数1(全 4 頁)

(21) 出願番号 特願平3-41872

(22) 出願日 平成3年(1991)3月7日

(71) 出願人 590000455

財団法人石油産業活性化センター
東京都港区麻布台2丁目3番22号

(71) 出願人 000105567

コスモ石油株式会社
東京都港区芝浦1丁目1番1号

(72) 発明者 水谷 昇

埼玉県草加市花栗4-20-3-101

(72) 発明者 金井 作信

茨城県岩井市矢作3004-67

(72) 発明者 山田 重久

埼玉県越谷市大沢2856-1 センチュリー
マンション磯崎403号

(74) 代理人 井理士 有賀 三幸 (外2名)

(54) 【発明の名称】 液冷式内燃機関用ロングライフクーラント組成物

(57) 【要約】

【構成】 防錆剤およびヒドラジンを含有し、炭素数2～9のグリコールを主成分とする液冷式内燃機関用ロングライフクーラント組成物。

【効果】 この液冷式内燃機関用ロングライフクーラント組成物は高温条件で使用しても長時間安定であり、優れた耐熱性および耐食性を有し、ディーゼル機関等の内燃機関に使用される冷却液のクーラントとして極めて有用である。

【特許請求の範囲】

【請求項1】 防錆剤およびヒドラジンを含含有し、炭素数2～9のグリコールを主成分とする液冷式内燃機関用ロングライフクーラント組成物。

【発明の詳細な説明】

【0001】

【産業上の利用分野】 本発明は、ディーゼル機関等の内燃機関の液冷式冷却装置に使用される、優れた耐熱性及び耐食性を有する液冷式内燃機関用ロングライフクーラント組成物（以下「LLC」という）に関する。

【0002】

【従来の技術および発明が解決しようとする課題】 近年、省エネルギーを目的として様々なトータルエネルギーシステムの開発が盛んに行われている。例えば、ディーゼル機関等の内燃機関においては、高温になった冷却液の熱を他の熱源に利用している。この場合、冷却装置としてはエネルギー効率の向上を目的として、通常従来の開放循環式に代えて、密閉循環式の冷却装置が使用され、また冷却液の温度も約100～130℃の高温で使用されることがある。従って、一般にこの高温の冷却液による冷却装置の防食を目的として種々の防錆剤が添加されているが、使用温度が高温であるため防錆剤の熱劣化あるいは酸化劣化が発生し、冷却液の色相悪化、スラッジ生成および防錆能力低下等の問題が生じている。また、この問題を解決することを目的として、耐熱性の防錆剤およびそれを含有するLLC等の開発もなされてきたが、未だ十分満足し得るものは得られていなかった。

【0003】 従って、本発明は約100～130℃の高温条件下で使用しても長時間安定で、耐熱性および耐食性に優れたLLCを開発することを課題とする。

【0004】

【課題を解決するための手段】 斯かる実情において、本発明者らは前記課題を解決すべく鋭意検討した結果、防錆剤およびヒドラジンを含含有し、炭素数2～9のグリコールを主成分とするクーラント組成物が高温条件下で使用しても長期間安定で、耐熱性および耐食性に優れることを見出し本発明を完成した。

【0005】 すなわち、本発明は防錆剤およびヒドラジンを含含有し、炭素数2～9のグリコールを主成分とするLLCを提供するものである。

【0006】 本発明に用いられる防錆剤は、通常の内燃機関用冷却液の防錆剤として使用できるものであれば、いずれをも使用することができ、例えばメルカプトベンゾチアゾール、メチルベンゾトリアゾール、アルキルイミダゾリン、ジエタノールアミン、安息香酸ソーダおよびそれらの混合物等を挙げることができる。斯かる防錆剤の、本発明LLC全量中の配合割合は、使用する防錆剤の種類によって異なるが、一般的には約0.1～7重量%（以下単に「%」と称する）であり、特に約0.5～6%が好ましい。配合割合が0.1%未満であると防錆効果が

十分得られず、また7%を超えても著しい防錆効果の向上は見られない。

【0007】 また、本発明に用いられるヒドラジンは、前述の防錆剤が、高温下で熱劣化あるいは酸化劣化するのを防止し、耐食性の向上を目的として添加するものである。ヒドラジンの本発明LLC全量中の配合割合は、約0.001～1%、特に約0.01～0.05%が好ましい。配合割合が0.001%未満であると防錆剤の劣化防止効果が十分得られず、また1%を超えても著しい劣化防止効果の向上は見られない。

10

【0008】 更に、本発明のLLCの主成分である炭素数2～9のグリコールは、内燃機関を停止し、冷却液が低温となった場合の凍結防止を目的とする凍結防止剤として使用されるもので、具体的にはエチレングリコール、ジエチレングリコール、トリエチレングリコール、プロピレングリコール、ジプロピレングリコール、トリプロピレングリコール等を挙げることができる。斯かるグリコールの本発明LLC全量中における配合割合は約90～99.999%が好ましい。

20

【0009】 本発明のLLCは、通常のクーラント組成物と同様、上述の各成分を混合することにより得ることができる。

【0010】 斯くして得られた本発明のLLCをディーゼル機関等の冷却液（通常は水が用いられる。）に用いる場合、単に本発明のLLCを冷却液中に添加すればよい。その添加量は通常の不凍液の添加量と同程度でよく、一般に冷却液全量中、約10～50%であり、特に約20～40%が好ましい。

30

【0011】 本発明のLLCは、約100～130℃の高温条件下で使用しても長時間安定で、優れた耐熱性および耐食性を有しているが、これはヒドラジンの添加により高温下における防錆剤の熱劣化あるいは酸化劣化を防止できるとともにヒドラジン自体が防錆剤として作用しているためと考えられる。

【0012】

【発明の効果】 本発明のLLCは高温条件下で使用しても長時間安定であり、優れた耐熱性および耐食性を有し、ディーゼル機関等の内燃機関に使用される冷却液のクーラントとして極めて有用である。

40

【0013】

【実施例】 以下、実施例により本発明を更に詳細に説明するが、本発明はこれら実施例によって何ら限定されるものではない。

【0014】 実施例1

表1に示す組成のLLC各々120ccを水道水280ccに添加した水溶液を用いて、温度120℃にて、空気吹き込みを行わず加圧密閉系とし、サンプル充填率を40%、試験時間を336時間とした以外はJIS K-2234に示す金属腐食性試験法に従って、スラッジ量の測定および試験後の色相の目視判定を行うことにより、耐食性能の評価を行っ

50

(3)

特開平4-279690

4

た。その結果を表2に示す。

【0015】

【表1】

【0016】

【表2】

組成物名 成分		本 発 明 品						比 較 品					
		1	2	3	4	5	6	1	2	3	4	5	6
タルカプトベンゾチアゾール			3		3		6				3		6
アルキルイミダゾリン		3		3		6				3		6	
ヒドラジン		0.03	0.03	0.05	0.05	0.03	0.03		0.5				
エチレンジグリコール		96.97	95.97	96.95	96.95	93.97	93.97	100	99.5	97	97	94	94

10

20

30

40

組成物No	スラッジ量 (ppm)	試験後の式相
本発明品 1	70	淡黄色
本発明品 2	80	淡黄色
本発明品 3	30	透 明
本発明品 4	40	透 明
本発明品 5	60	淡黄色
本発明品 6	70	淡黄色
比較品 1	280	茶
比較品 2	270	濃 黄
比較品 3	250	濃 黄
比較品 4	350	茶
比較品 5	220	濃 黄
比較品 6	300	茶

【0017】表2の結果から明らかな如く、本発明品を用いた場合の方が比較品を用いた場合よりもスラッジ発生量および色相の変化が少ない。このことより本発明の

LLCは、120℃の高温で長期間使用しても安定で、耐熱性および耐防食性に優れていることがわかる。